

## PRODUCT DATA SHEET

# Sika® ViscoCrete®-900 NT

### 3RD GENERATION LOW-MID RANGE SUPERPLASTICIZER

#### DESCRIPTION

Sika® ViscoCrete®-900 NT is a third generation low-mid range superplasticizer for concrete and mortar. It meets the requirements for superplasticizers according to ASTM C494 type G.

#### USES

Sika® ViscoCrete®-900 NT is suitable for the production of site mixed as well as ready-mix concrete.

Sika® ViscoCrete®-900 NT is used for concrete with extended transportation or placing time.

Sika® ViscoCrete®-900 NT facilitates good water reduction, excellent flow properties optimal cohesion and highest self compaction behaviour.

Sika® ViscoCrete®-900 NT is used for the following types of concrete:

- Hot weather concrete and concrete with extended transportation or placing time
- Concrete with highest water reduction (10-15% typical)
- High strength concrete
- Grade 30-40 mpa low medium-high workability concrete, 125 mm -180 mm slump

High water reduction and excellent flowability have a positive influence on the above mentioned applications.

#### CHARACTERISTICS / ADVANTAGES

Sika® ViscoCrete®-900 NT acts by different mechanisms. Through surfaceabsorption and sterical separation effect on the cement particles, in parallel to the hydration process, the following properties are obtained:

- High water reduction (resulting in high density and strengths)
- Excellent flowability (resulting highly reduced placing and compacting efforts)

#### PRODUCT INFORMATION

<b>Chemical Base</b>	Polycarboxylic polyether type polymer
<b>Packaging</b>	210 L/drum, 1000 L/bulk
<b>Shelf Life</b>	12 months from date of production if stored properly in unopened, undamaged, original container.
<b>Storage Conditions</b>	Protect from direct sunlight at temperatures between +5°C and +35°C
<b>Density</b>	1.09 kg/L typical

## APPLICATION INFORMATION

### Recommended Dosage

For plastic concrete:

1.0-1.5% by weight of  
cement binder

## APPLICATION INSTRUCTIONS

Sika® ViscoCrete®-900 NT is added to the gauging water or simultaneously poured into the concrete mixer. For optimum utilization of the high water reduction we recommend thorough mixing at a minimal wet mixing of 60 seconds. The addition of the remaining gauging water – to fine tune concrete consistency - may only be started after 2/3 of the wet mixing time, to avoid surplus water in the concrete.

### DISPENSING

With the use of Sika® ViscoCrete®-900 NT concrete of highest quality is being produced. The standard rules of good concreting practice (production as well as placing) must also be observed with Sika® ViscoCrete®-900 NT concrete.

Fresh concrete must be cured properly.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

**Sika Philippines Inc.**  
888 Marcos Alvarez Ave.,  
Talon V, Las Piñas City, Philippines 1747  
Tel. No.: +63 2 8806-2875  
Fax. No.: +63 2 8806-2883  
Website: [phl.sika.com](http://phl.sika.com)

Product Data Sheet  
Sika® ViscoCrete®-900 NT  
March 2019, Version 01.01  
021301011000000786

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaViscoCrete-900NT-en-PH-(03-2019)-1-1.pdf