

## PRODUCT DATA SHEET

# SikaSwell® A (AE)

(formerly MSeal 910)

Hydrophilic swellable joint sealing profiles

## **DESCRIPTION**

SikaSwell® A (AE) is a rectangular acrylic sealing profile. It swells in contact with water to seal all types of construction joints and penetrations in concrete structures.

## **USES**

Joint sealing:

- Construction joints
- Pipe and steel work penetrations through walls and floor slabs
- Around all types of penetrations and connection ioints
- Construction joints in cable ducts

## **CHARACTERISTICS / ADVANTAGES**

- Highly economical joint sealing solution
- Unique properties, fills the small cracks and voids
- Versatile solution for joints and details
- Permanently water resistant (wet & dry cycles)
- Resistant to various chemical substances
- Easy and fast to apply
- Can be applied on different substrates
- Available in different sizes

## **ENVIRONMENTAL INFORMATION**

 Conforms with LEED v4 MR credit: Building product disclosure and optimization — Material ingredients (option 2)

## **PRODUCT INFORMATION**

Chemical Base	Acrylic polymer					
Packaging	Single rolls packed in vacuum foil. Multiple single rolls packed in cardboard boxes. Refer to current price list for packaging variations.					
Shelf Life	12 months from the date of production					
Storage Conditions	The product must be stored in original, unopened and undamaged packaging in dry conditions at temperatures between +5°C and +35°C. Always refer to packaging.					
Density	~1.50 kg/l (at +23°C)					
Dimensions	Туре	Width	Height	Length		
	SikaSwell® A (AE) 2005	20 mm (±10 %)	5 mm (±5 %)	20 m		
	SikaSwell® A (AE) 2010	20 mm (±10 %)	10 mm (±5 %)	10 m		

Product Data Sheet SikaSwell® A (AE) January 2025, Version 04.01 020703000060002005

## **TECHNICAL INFORMATION**

Service Temperature	Maximum	+50°C	+50°C -20°C		
	Minimum	-20°C			
Change of volume	Time	Demineralised water	(EN 14498		
	1 day	~50 %	<del>_</del>		
	7 days	~130 %	<del>_</del>		
	30 days	~150 %			
	Note: Swelling properties in saline water will be reduced and delayed. Use SikaSwell® A Maritim version.  Note: In a totally dry state the Product shrinks to its original dimensions.  The product then expands again upon further contact with water.				
Swelling pressure	The pressure devel	oped by the material depends on th	a stiffness of the		
orreining procedure	surrounding concre ity, voids, gaps and	ite structure, which is influenced by other weaknesses. ncrete structure the material can de	the concrete qual-		
	surrounding concre ity, voids, gaps and Note: In an ideal co pressure of >10 bar	ite structure, which is influenced by other weaknesses. ncrete structure the material can de	the concrete qual-		
APPLICATION INFORMA  Ambient Air Temperature	surrounding concre ity, voids, gaps and Note: In an ideal co pressure of >10 bar	ite structure, which is influenced by other weaknesses. ncrete structure the material can de	the concrete qual-		
APPLICATION INFORMA	surrounding concre ity, voids, gaps and Note: In an ideal co pressure of >10 bar	te structure, which is influenced by other weaknesses. ncrete structure the material can de	the concrete qual-		
APPLICATION INFORMA	surrounding concre ity, voids, gaps and Note: In an ideal co pressure of >10 bar TION	te structure, which is influenced by other weaknesses. ncrete structure the material can de	the concrete qual-		
APPLICATION INFORMA  Ambient Air Temperature	surrounding concre ity, voids, gaps and Note: In an ideal co pressure of >10 bar TION Maximum Minimum	te structure, which is influenced by other weaknesses.  ncrete structure the material can de  +35°C +5°C	the concrete qual-		

Adhesive

Swelling profile

## **BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## **LIMITATIONS**

**System Structure** 

- Do not use SikaSwell® A (AE) profiles for movement ioints.
- SikaSwell® A (AE) profiles expand when in contact with water. This is not instantaneous and will take a few hours
- The Product is recommended for sealing against water pressures up to 2 bar. For pressures higher than 2 bar, use an alternative or supplementary Sika Joint Sealing solution or contact Sika Technical Services for further information.

## **ECOLOGY, HEALTH AND SAFETY**

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

SikaSwell® S-2

SikaSwell® A (AE)

Product Data Sheet SikaSwell® A (AE) January 2025, Version 04.01 020703000060002005



## APPLICATION INSTRUCTIONS

#### SUBSTRATE QUALITY

The substrate must be sound, clean, dry or matt damp, free from all surface contaminants that could impair the adhesion.

#### SUBSTRATE PREPARATION

#### **EXISTING CONCRETE**

Rough surfaces are susceptible to leaking. If the surface roughness cannot be leveled with SikaSwell® S-2 the roughness shall be leveled with an appropriate Sika leveling mortar or by mechanical treatment, before the SikaSwell® S-2 and SikaSwell® profile is applied.

#### FRESHLY CAST CONCRETE

Freshly cast concrete can be smoothed with a batten where SikaSwell® S-2 is to be placed.

#### **APPLICATION**

#### **IMPORTANT**

#### Concrete cover

Insufficient concrete cover, low density concrete or voids will prevent the SikaSwell® A (AE) from developing its waterproofing function.

- Place the SikaSwell® profile in the centre of the concrete structure.
- 2. In reinforced concrete maintain a minimum cover of 8 cm on both sides.
- 3. In unreinforced concrete maintain a minimum cover of 15 cm on both sides.

#### Sealant with SikaSwell® A (AE)

- 1. Apply SikaSwell® S-2 adhesive in a narrow bed (size of triangular section ~12 mm tall and ~12 mm wide ) onto the prepared substrate. Extrude enough material to level the roughness of the substrate.
- 2. Press the SikaSwell® A (AE) firmly into the fresh applied SikaSwell® S-2. Place the SikaSwell® A (AE) within a maximum of 30 minutes (+23 °C / 50 % r.h.).
- 3. Ensure full and continuous contact between the SikaSwell® S-2 and both the SikaSwell® A (AE) and the substrate is achieved.
- 4. Allow SikaSwell® S-2 to harden minimum 12 hours before placing concrete. For pouring height > 50 cm, SikaSwell® S-2 must harden for at least 24 hours before placing concrete.
- 5. Protect the SikaSwell® S-2 and the SikaSwell® A (AE) against water (for example, rain) until the concrete is placed.
- 6. During placement compact the fresh concrete well around the SikaSwell® A (AE) to achieve dense concrete without any honeycombing or voids.

## Sika Philippines Inc.

888 Cayetano Avenue, C5 Extension, Brgy. Palingon - Tipas Taguig City, Philippines 1630 Telephone no. +63 2 8790-9800 Fax no. +63 2 8790-9828

#### **CLEANING OF TOOLS**

Clean all tools and application equipment immediately after use with Sika® Colma Cleaner. Hardened material can only be removed mechanically.

## **LOCAL RESTRICTIONS**

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields

## **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaSwellAAE-en-PH-(01-2025)-4-1.pdf



January 2025, Version 04.01 020703000060002005