

PRODUCT DATA SHEET

Sika® FerroGard® CI 222

(formerly MasterLife® CI 222)

Organic corrosion inhibiting admixture

DESCRIPTION

Sika® FerroGard® CI 222 is an organic migratory corrosion inhibiting admixture formulated to inhibit the corrosion of steel reinforcement in concrete. Sika® FerroGard® CI 222 provides two levels of corrosion protection, inhibiting and waterproofing.

Sika® FerroGard® CI 222 functions by inhibiting corrosion at its most critical points. Sika® FerroGard® CI 222 lines the pores of the concrete matrix thus waterproofing and slowing the rate at which chlorides and moisture enter the concrete and denying the corrosion process of its two most important components. Suitable to use in hot and tropical climatic conditions.

USES

Sika® FerroGard® CI 222 typical uses:

- Concrete bridges, highways and pavements exposed to de-icing salts.
- Concrete marine structures operating in chloride environments.
- Concrete tunnels, infrastructure or retaining walls.
- Concrete in industrial plants where corrosive substances are present.
- Concrete parking structures and decks.
- Concrete piers, piles, caissons and dock structures.

PRODUCT INFORMATION

Packaging	200 L drums and bulk if required
Shelf Life	12 months from date of production if stored in unopened original container in a dry and frost-free condition
Storage Conditions	Store in undamaged, unopened, original sealed packaging in dry conditions at temperatures between +5°C and +50°C. Mix well before using.
Appearance / Colour	colorless to white liquid
Specific gravity	0.995 to 1.100

CHARACTERISTICS / ADVANTAGES

Sika® FerroGard® CI 222 increases the life expectancy and durability of reinforced concrete by slowing the ingress of chlorides and moisture into the concrete and by forming a strong, durable protective film on the reinforcing steel for a second level of corrosion protection.

This protective film slows the corrosion process by preventing chlorides from reacting with the reinforcing steel, and by depriving the corrosion process of moisture and oxygen, thus slowing the rate of corrosion once it begins.

This dual mechanism system makes Sika® FerroGard® CI 222 effective with all supplementary cementitious materials, as well as in cracked concrete where the elements that cause corrosion have direct access to the reinforcing steel.

TECHNICAL INFORMATION

Concreting Guidance

The standard rules of good concreting practice for production and placing must be observed when using Sika® FerroGard® CI 222 in concrete. Refer to relevant standards.

Fresh concrete must be cured properly especially at high temperatures in order to prevent plastic and drying shrinkage. Use Sika® Antisol® products as a curing agent or apply wet hessian.

APPLICATION INFORMATION

Recommended Dosage

5 L/m³ of concrete for all applications and corrosion environments. Sika® FerroGard® CI 222 dosed at 5 L/m³ is formulated to provide optimum corrosion protection of reinforced concrete structures in severe corrosive environments and therefore provides excellent corrosive protection in less severe corrosion environments as well.

Sika® FerroGard® CI 222 is formulated for use at a single dosage in order to eliminate the confusion and uncertainties related to determining the severity of the corrosive environment and predicting the chloride exposure of the structure.

Dispensing

Sika® FerroGard® CI 222 may be added with concrete batch water. It should not be mixed with any other admixtures prior to being introduced into the concrete mixer. The use of this admixture does not require changes in normal batching procedures.

Compatibility

Sika® FerroGard® CI 222 is suitable for mixes containing all types of cement and supplementary cementitious materials such as Microsilica (Silica Fume), Fly Ash (PFA), GGBS (ground granulated blast furnace slag) and the following Sika products:

SikaPlast®, Sika® ViscoCrete®, Sikament®, Plastiment®, SikaPump®, SikaFume®, SikaFiber®, Sika® Aer, Sika® Stabilizer, SikaControl®
We recommend to perform trial mixes to establish the required performance when combining Sika® FerroGard® CI 222 with the above products or other admixtures. Please consult our Sika Technical Department.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

Sika® FerroGard® CI 222 has no effect on slump or the temperature development profile of concrete.

Concrete to steel bond strength is not affected by Sika® FerroGard® CI 222. Additional protection can be attained through the use of high-range water-reducing admixtures to provide adequate placeability and consolidation at low water-cement ratios and/or the use of supplementary cementitious material to reduce concrete permeability.

Sika® FerroGard® CI 222 will not initiate or promote corrosion of reinforcing steel embedded in concrete, prestressed concrete or concrete placed on galvanised steel floor and roof systems. Neither calcium chloride nor any chloride-based ingredients are used in the manufacture of Sika® FerroGard® CI 222 corrosion inhibiting admixture.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Philippines Inc.

888 Cayetano Avenue,
C5 Extension, Brgy. Palongon - Tipas
Taguig City, Philippines 1630
Telephone no. +63 2 8790-9800
Fax no. +63 2 8790-9828

Product Data Sheet

Sika® FerroGard® CI 222
September 2024, Version 01.01
02140300000002092

SikaFerroGardCI222-en-PH-(09-2024)-1-1.pdf

