

# PRODUCT DATA SHEET

## Sika<sup>®</sup> Boom AP

### MULTI-POSITION, HIGH YIELD EXPANDING FOAM

#### DESCRIPTION

Sika<sup>®</sup> Boom AP is a 1-component, fast curing polyurethane foam suitable for multi-position applications.

#### USES

Sika<sup>®</sup> Boom AP is used for fixing, insulating and filling connection joints around window and door frames, pipe entries, air conditioning vents and roller blind housings, etc.

Sika<sup>®</sup> Boom AP allows insulation against noise, cold and draught after single application

#### CHARACTERISTICS / ADVANTAGES

- Multi-positioning foam; application in all positions (360°C)
- High Expansion rate
- Fast-curing
- Easy application with nozzle
- Very good thermal and sound insulation
- Can be cut, sanded and over painted ( overpaintability test must be done)
- HFC-free

#### PRODUCT INFORMATION

<b>Chemical Base</b>	Polyurethane
<b>Packaging</b>	Available in 500ml & 750ml
<b>Colour</b>	Light Yellow
<b>Shelf Life</b>	Sika <sup>®</sup> Boom AP has a shelf life of 18 months from the date of production, if stored properly in undamaged, original, sealed packaging, and if the storage conditions are met. Opened cans of Sika <sup>®</sup> Boom AP must be used within 4 weeks.
<b>Storage Conditions</b>	Sika <sup>®</sup> Boom AP shall be stored in an upright position, in dry conditions, protected from direct sunlight and at temperatures between +5 °C and +25 °C.
<b>Density</b>	~24 kg/m <sup>3</sup>

#### TECHNICAL INFORMATION

<b>Compressive Strength</b>	~0.04 N/mm <sup>2</sup> (with 10% deformation)	(ISO 844)
<b>Tensile Strength</b>	~0.01 N/mm <sup>2</sup>	(ISO 1926)
<b>Elongation at Break</b>	~28 %	
<b>Shear Strength</b>	~0.04 N/mm <sup>2</sup>	(ISO 1922)
<b>Dimensional Stability</b>	± ~5 %	

<b>Joint Permeability to Water Vapour</b>	$\mu = 21$ , $sd = 1.0$ m ( $d = 49$ mm, $p = 19.5$ kg/m <sup>3</sup> )	(ISO 12572)
<b>Thermal Conductivity</b>	~0.030 W/mK	(EN 12667)
<b>Service Temperature</b>	-40 °C min. / +80 °C max.	

## APPLICATION INFORMATION

<b>Yield</b>	500ml	~25L
	750ml	~38L
Consumption can be regulated by adjusting the pressure on the valve.		
<b>Ambient Air Temperature</b>	Optimum	+20°C
	Permissible	+5 °C min. / +40 °C max.
<b>Substrate Temperature</b>	Optimum	+20°C max.
	Permissible	+5 °C min. / +40 °C max.
<b>Curing Time</b>	Sika® Boom AP is fully cured after 24 hours.	
<b>Cutting Time</b>	~30-60 minutes depending on ambient humidity and temperature levels.	
<b>Tack Free Time</b>	~10 minutes depending on ambient humidity and temperature levels.	

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

The substrate must be clean, sound and homogeneous, free from oils, grease, dust and loose or friable particles. Paint, cement laitance and other poorly adhering contaminants must be removed. Sika® Boom AP adheres without primers and/or activators. Pre-dampen the substrate with a mist spray of clean water, this ensures that the foam cures properly and also prevents secondary foam expansion.

### APPLICATION METHOD / TOOLS

Shake the Sika® Boom AP can well for minimum 20 seconds before use. Screw application trigger straw nozzle onto the valve of the can. Repeat shaking after long interruptions of use. The amount of expanding foam extruded can be regulated by applying more or less pressure on the trigger. Fill deep joints in several layers. Take care to allow each layer to cure and expand sufficiently by spraying water between each layer or allowing sufficient waiting time between the layers. Do not fill hollow sections completely as the foam expands during curing. All building elements must be temporarily fixed until the foam has fully cured.

### CLEANING OF TOOLS

Clean all tools and application equipment immediately with Sika® Boom Cleaner and/or Sika® Remover-208 or equivalent. Once cured, residual material can only be removed mechanically.

## FURTHER DOCUMENTS

### FURTHER DOCUMENTS

- Safety Data Sheet (SDS)

## LIMITATIONS

### LIMITATIONS

- The can temperature for application must be +10 °C
- In order to get a good quality foam, the can temperature should not vary more than 10 °C from the ambient temperature
- Protect the can from direct sunlight and temperatures above +50 °C (danger of explosion)
- For correct curing of the foam, moisture is necessary. Applying insufficient moisture may lead to subsequent unintended foam expansion (post expansion)
- Do not fill hollow sections completely as the foam expands during curing
- Do not use on polyethylene (PE), polypropylene (PP), polytetrafluoroethylene (PTFE / Teflon), and silicone, oil, grease and other separating agents
- Sika® Boom AP is not resistant to UV light.
- Read all safety and technical recommendations which are printed on the Sika® Boom AP can.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika Philippines Inc.**  
888 Marcos Alvarez Ave.,  
Talon V, Las Piñas City, Philippines 1747  
Tel. No.: +63 2 8806-2875  
Fax. No.: +63 2 8806-2883  
Website: [phl.sika.com](http://phl.sika.com)

Product Data Sheet  
Sika® Boom AP  
July 2019, Version 01.02  
020514060000000016

SikaBoomAP-en-PH-(07-2019)-1-2.pdf

