

## PRODUCT DATA SHEET

# Sika® Stabilizer-301 UWC PH

## UNDERWATER/ANTI-WASHOUT ADMIXTURE

### DESCRIPTION

Sika® Stabilizer-301 UWC PH is a powdered underwater / anti-washout admixture formulated to increase the cohesion of concrete to enable significant reductions in washout.

### USES

Sika® Stabilizer-301 UWC PH allows for the production and the improvement of concrete to be placed underwater.

Sika® Stabilizer-301 UWC PH is mainly used for the following applications:

- A wide range of applications where concrete is to be placed underwater.
- Marine construction

### CHARACTERISTICS / ADVANTAGES

Sika® Stabilizer-301 UWC PH has the following characteristics and should be used in combination with a Sika® HRWR/ Superplasticiser:

- Strong increase in cohesion
- Extended workability
- Superior anti-washout properties
- Provides improved integrity of concrete placed underwater
- Less segregation and bleed

### PRODUCT INFORMATION

<b>Chemical Base</b>	Powder blend of plasticizers and viscosity modifiers
<b>Packaging</b>	4 kg/pack 3 packs/box (12kg)
<b>Shelf Life</b>	12 months from date of production if stored properly.
<b>Storage Conditions</b>	Store properly in unopened and undamaged original sealed containers protected from direct sunlight & moisture at temperatures between +5°C and +30°C.
<b>Appearance / Colour</b>	Broken White Powder
<b>Density</b>	~0.667 Kg/L

### APPLICATION INFORMATION

<b>Consumption</b>	0.5 – 1.5 % by weight of total cementitious binder (depend on mix design and material)
--------------------	--

## Compatibility

Sika® Stabilizer-301 UWC PH may be combined with many other Sika products.

### Important:

Always conduct trials before combining products in specific mixes and contact our Technical Service Department for information about specific combinations.

---

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## USES

When using Sika® Stabilizer-301 UWC PH a suitable mix design has to be taken into account and local material sources shall be trialed.

Overdosing may cause an increase in air-entrainment that will tend to lower the compressive strength. Cohesion and anti-washout properties will be increased which may lead to reduced workability of the concrete. There may also be an increase in set time.

The compressive strength of underwater concrete may be slightly reduced by the inclusion of Sika® Stabilizer-301 UWC PH but this is often negated by the addition of a Sika® HRWR/Superplasticizer.

The setting time of underwater concrete will be increased when Sika® Stabilizer-301 UWC PH is used. This extra time to set is often beneficial to the concreting operation as underwater concrete pours generally take longer to complete than conventional land-based pours.

The air-content of the underwater concrete may be increased slightly due to the viscous nature of the mortar matrix preventing all entrapped air being released.

Support from our Technical Service Department is recommended.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet containing physical, ecological, toxicological and other safety related data.

## APPLICATION INSTRUCTIONS

### DISPENSING

Sika® Stabilizer-301 UWC PH should not be added to the gauging water.

Sika® Stabilizer-301 UWC PH should preferably be added at the batching plant with the aggregate or cement to support dispersion.

A wet mixing time, which is depending on the mixing conditions and mixer performance, of at least 120 seconds is recommended.

Underwater concrete needs to have high workability (F4 consistence) in order to flow and compact. Underwater/anti-washout admixtures combined with superplasticizers require a long, slower mixing action to achieve a high workability.

When added directly to a truck mixer, the mixer shall rotate its drums at maximum revolutions for at least 1 minute per m<sup>3</sup> concrete and a minimum of 5 minutes to achieve a uniform mix.

### APPLICATION

The standard rules of good concreting practice, concerning production and placing, are to be followed. Cement contents should be at least 400 kg/m<sup>3</sup> (CEM I) with a maximum water/cement ratio of 0.45.

Typically, the fine aggregate content should be >45%. Laboratory trials shall be carried out before concreting on site, especially when using a new mix design or producing new concrete components.

Underwater concrete can be placed by skip, pump or tremie. However, care is needed not to allow the concrete to free-fall through a water filled pump line or tremie pipe as the turbulent flow produced will cause the mix to segregate. Pumping will normally produce the best results and minimize washout as only the top surface is usually exposed to the full effects of the water movement.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika Philippines Inc.**  
888 Marcos Alvarez Ave.,  
Talon V, Las Piñas City, Philippines 1747  
Tel. No.: +63 2 8806-2875  
Fax. No.: +63 2 8806-2883  
Website: [phl.sika.com](http://phl.sika.com)

**Product Data Sheet**  
Sika® Stabilizer-301 UWC PH  
January 2024, Version 01.01  
021403031000000127

SikaStabilizer-301UWCPH-en-PH-(01-2024)-1-1.pdf

