

PRODUCT DATA SHEET

Sika Waterbar® AR VN

EXTERNAL PVC WATERBAR FOR CONSTRUCTION JOINTS

DESCRIPTION

Sika Waterbar® AR VN is a flexible, external waterbar for construction joints made from thermoplastic PVC. It is designed to stop the migration of water through construction joints in concrete structures.

USES

For the effective sealing of concrete construction joints in structures such as:

- Water reservoirs
- Sewage treatment plants
- Swimming pools
- Basements
- Retaining walls
- Lift shafts
- Tunnels, culverts
- Service pits

PRODUCT INFORMATION

Packaging	20 m rolls (other lengths on request)
Shelf Life	5 years from date of production if stored properly
Storage Conditions	Dry, shaded place (protected from sunlight)
Appearance / Colour	Flexible strip / Yellow

SYSTEM INFORMATION

System Structure	Type	Width mm (± 5mm)	Roll Length (m)	Nominal Thickness mm (± 10%)	Height of ribs (mm) (± 5mm)
	AR-25	250	20	2.5 - 4.0	20


Sika Waterbar® AR-25 VN profile

CHARACTERISTICS / ADVANTAGES

- Sealing starts as soon as the concrete has hardened
- Multi rib profile provides impenetrable barriers to water migration
- Can be easily site welded (welding knife is available)
- Good chemical resistance
- Integrated injection channels for subsequent back-filling
- Suitable for welding with PVC-P based Sikaplan® WP membranes

APPROVALS / STANDARDS

Local test reports (in Vietnam) are available.



TECHNICAL INFORMATION

Shore A Hardness	> 70	ASTM D2240
Tensile Strength	12 N/mm ² (± 5%)	ASTM D412-06
Elongation	300% (± 5%)	ASTM D412-06
Service Temperature	-35°C to +55°C	
Chemical Resistance	Permanent: Seawater, sewage Temporary: Diluted inorganic alkalis, mineral acids, mineral oils and fuels.	

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS

- Level differences, bends, junctions, etc. should be carefully considered before placing.
- The quality of the joint sealing depends on the fully enclosure of the waterbar with concrete. In order to obtain a qualitative embedding, gravel nests have to be avoided.
- If there are very high stresses or difficult concreting conditions, the waterbars can be combined with integrated injection hoses installed locally on the top of the anchoring ribs to additionally inject / grout around the cast-in parts at a later date.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

Application

The Sika Waterbar® AR VN profile is installed flush with the external face of the concrete. It should be carefully fixed in the formwork before concreting. The Sika Waterbar® AR VN should be aligned and installed on the waterproofing substrate as centrally as possible to the segment joint.

Protection until the waterbar system is fully cast in the concrete.

Special care must be taken with the waterbar system ends.

Waterbars must be cleaned before casting in.

Do not install on the top surface of horizontal or slightly sloping concrete.

Welding

The Sika Waterbar® AR VN is butt jointed by welding at minimum ambient temperature of + 5°C and dry weather conditions.

Jointing with adhesives is not permitted.

On site welding can be undertaken using a Sika electric welding knife. The specific welding parameters must be adjusted and checked on samples prior to the welding work.

Both ends of the joint are heated simultaneously on the faces of the welding knife until an even, molten bead of PVC appears. The welding knife is withdrawn and the Sika Waterbar® AR VN is immediately pushed together.

The joint should be held rigid until the plastic cools down and solidifies.

Check for any gaps or imperfect joints.

Failures can be caused by irregularities of cut edges, insufficient heat, over heated, dust etc.

Redo the welding if necessary.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Philippines Inc.
888 Marcos Alvarez Ave.,
Talon V, Las Piñas City, Philippines 1747
Tel. No.: +63 2 8806-2875
Fax. No.: +63 2 8806-2883
Website: phl.sika.com

Product Data Sheet
Sika Waterbar® AR VN
June 2023, Version 01.02
020703100100000175

SikaWaterbarARVN-en-PH-(06-2023)-1-2.pdf

