

BUILDING TRUST

PRODUCT DATA SHEET Sika[®] Separol[®]-10 PH

CHEMICAL FORM RELEASE AGENT

DESCRIPTION

Sika® Separol® -10 PH is form release agent.

USES

Form release agent for steel and wooden formwork. Sika® Separol®-10 PH facilitates removal and cleaning of shuttering. Number of lifts is substantially increased.

PRODUCT INFORMATION

CHARACTERISTICS / ADVANTAGES

- Ready to use
- Easy to apply
- Combined chemicals and physical action
- Ensure fair faced concrete finish
- No staining
- Suitable also for use on formwork used in steam curing process.

Chemical Base	Oil Base	
Packaging	210 L drums	
Shelf Life	12 months from date of production if stored properly in undamaged un- opened, original sealed packaging.	
Storage Conditions	Stored in dry conditions at temperature +30 °C maximum.	
Appearance / Colour	Reddish / Yellow Liquid	
Specific gravity	0.83 ± 0.02 kg/L	

APPLICATION INFORMATION

Consumption	On Timber / plywood formwork	1L~20-25 m ²
	On metal or plastic formwork	1 L for ~40 m ²

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

All surfaces to be coated with Sika[®] Separol[®]-10 PH must be clean and free from grease and old concrete.

APPLICATION METHOD / TOOLS

Apply one uniform, thin coat of Sika[®] Separol[®]-10 PH by brush, roller or spray equipment, on dry or damp formwork.

To achieve optimum result it is recommended to pour the concrete minimum 4 hours after Sika[®] Separol[®]-10 PH application.

APPLICATION

LIMITATIONS

- Protect fresh coat from rain.
- Cleaning the mould surface between each use and before application is essential to prevent the formation of hardened concrete "build up".
- Sika[®] Separol[®]-10 PH contains flammable materials and falls under the dangerous goods regulations (class 3).
- During application in confined areas, ditches, shafts etc. adequate ventilation must be provided. During its application open fire and other igniting agents (e.g. welding works) must be removed.
- In a liquid not fully cured state the thinner and the product contaminate water and should not get into drains, water and ground.

CLEANING OF TOOLS

Clean all tools and equipment with solvent.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Philippines Inc. 888 Marcos Alvarez Ave., Talon V, Las Piñas City, Philippines 1747 Tel. No.: +63 2 8806-2875 Fax. No.:+63 2 8806-2883 Website: phl.sika.com

 Sika® Separol®-10 PH

 April 2023, Version 01.01

 021405021000000399

SikaSeparol-10PH-en-PH-(04-2023)-1-1.pdf



BUILDING TRUST