

# PRODUCT DATA SHEET

# Sika® ViscoCrete® SKY 8749

(formerly MasterGlenium® SKY 8749)

New Generation High Range Water Reducing Admixture

## **DESCRIPTION**

Sika ViscoCrete SKY 8749 is a new generation high range water reducing admixture, based on chains of modified polycarboxylate ether, primarily developed for concrete industry where slump retention, high strength and durability are required in hot climate. The ability to work with very low water/cement ratio and still obtain extended slump retention allows for the manufacture of high quality concrete. Sika ViscoCrete SKY 8749 has no added chloride, meets ASTM C 494 requirements for Type G and it is also compatible with all cements meeting the ASTM standards.

#### **USES**

Sika ViscoCrete SKY 8749 is especially suitable for concrete which requires good workability and high early and final strengths, such as:

- Production of load bearing precast elements (e.g. bridge girders, piles, concrete housing);
- Self compacting concrete for precast;
- Low slump concrete;
- Structures constructed using travelling forms and slip forms;
- Hot weather concreting;
- In-situ casting of structural elements.

# **CHARACTERISTICS / ADVANTAGES**

- Rheoplastic concrete with the lowest water/cement ratio;
- No segregation or bleeding;
- Low vibration time required even in case of high reinforced concrete;
- Excellent surface appearance;
- Reduces risks of retempering concrete on job site with additional water and improves the engineering properties of concrete like early and ultimate strengths, modulus of elasticity, bond strength to steel, depths of carbonation, impermeability, resistance to chemical aggressive agents, shrinkage and creep.

## PRODUCT INFORMATION

Chemical Base	modified polycarboxylate ether
Packaging	205 liter Drum, 1000 liter Bulk
Shelf Life	12 months from date of production if stored properly in undamaged unopened, original sealed packaging.

Product Data Sheet Sika® ViscoCrete® SKY 8749 May 2024, Version 01.01 021301000000002995

Specific gravity	1.06 to 1.1
Appearance / Colour	Yellowish to Brown Liquid
	place away from ignition sources, heat or flame. Protect from direct sunlight.
Storage Conditions	Store in cool and dry conditions at temperatures above 0°C, well ventilated

#### APPLICATION INFORMATION

Recommended Dosage	Optimum dosage of Sika® ViscoCrete® SKY 8749 should be determined by
	site trials.  Recommended dosage: 0.3 – 1.2 liter per 100 kg of cementitious material  A higher dosage might be used if agreed by client, consultant. Stir well before use.
Dispensing	Sika® ViscoCrete® SKY 8749 is a ready-to-use admixture to be added to the concrete mix as a separate component. Optimal mixing water reduction is obtained if Sika® ViscoCrete® SKY 8749 is poured into the concrete mix right after the addition of the mixing water. Avoid adding the admixture to the dry aggregates.

#### **BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

# **ECOLOGY, HEALTH AND SAFETY**

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

#### LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

#### **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Philippines Inc.

888 Cayetano Avenue, C5 Extension, Brgy. Palingon - Tipas Taguig City, Philippines 1630 Telephone no. +63 2 8790-9800 Fax no. +63 2 8790-9828

SikaViscoCreteSKY8749-en-PH-(05-2024)-1-1.pdf

